

# AQUAVINTAGE 2C

## A COLOR + B ACTIVATOR



1L

5L

### PRODUCT DESCRIPTION

Aquavintage 2C is a new two component water-based reactive stain, especially suitable for ageing the wood in a fast, easy way. Aquavintage 2C is a positive stain, which accentuates the wood grain giving depth and a warm unique texture to the wood. Different colours are available to give the wood a unique and authentic aspect.

### TECHNICAL DATA

VISCOSITY	AS WATER
SOLID CONTENTS	DEPENDING ON THE COLOUR
DENSITY	+/- 1 KG/L
DILUTION	WATER
MIXING RATIO ACTIVATOR	1/1
AVAILABLE IN 8 COLOURS – SEE COLOR CHART	
CONFORMS EUROPEAN DECOPAINT DIRECTIVE 2010	

### PREPARATION

Sand the wood with grain 100-120 and remove the sanding dust carefully.

### USER TIPS

Mix the Aquavintage 2C (A) with the Activator Aquavintage 2C(B) 1part to 1part or 50/50. After mixing, the liquid can only be used for a few weeks. During the application of the stain, stir regularly. Apply plentifully using a spray-gun, roller or brush. Afterwards level off with a brush or roller.

Let Aquavintage 2C react for 4 to 6 hours and De-nib the raised wood grain with fine sanding paper..



### DRYING TIMES

Aquavintage 2C can be finished after +/- 12 hours. Drying and reaction times are dependent on the wood species, applied amount, environment temperature, ventilation.



### COVERAGE

10-15 m<sup>2</sup>/litre

### AFTER TREATMENT

Aquavintage 2C is a stain and gives no protection. Therefore always finish with a Hardwaxoil, Lacquer or Wax from the Ciranova range. If using a lacquer, please contact the technical service of Ciranova for additional information.

### PRODUCT INFORMATION

Storage life: 1 year in the original and well closed packaging.

Not frost durable.

Available in 8 colours.

### SPECIAL QUALITIES:

Aquavintage 2C is not frost durable, never store or transport the product under 5°C.

Only use stainless material. Wood preparation, the type of wood, quantity applied etc. may affect the final colour. For this reason always make a test first!

Ciranova<sup>®</sup> products are made for the professional user. The instructions specified in the data sheet are formulated after necessary tests were performed and after years of experience. However, they are drawn to our best knowledge and ability. The user must test the application of the product in the for him applicable conditions. Guarantee can not be derived out the text of this technical description.

### PRODUCED BY DEBAL COATINGS NV

Industrieweg 29 – B 8800 Beveren-Roeselare  
tel +32 (0) 51 30 11 40 fax +32 (0) 51 31 26 48  
www.ciranova.be ciranova@ciranova.be