



2,5L

Ciranova® products are made for the professional user. The instructions specified in the data sheet are formulated after necessary tests were performed and after years of experience. However, they are drawn to our best knowledge and ability. The user must test the application of the product in the for him applicable conditions. Guarantee can not be derived out the text of this technical description.

PRODUCED BY DEBAL COATINGS

NV

Industrieweg 29 - B 8800 Beveren-
Roeselare

tel +32 (0) 51 30 11 40 fax +32 (0) 51 31 26
48

www.ciranova.be

ciranova@ciranova.be

Hardwaxoil TITAN

PRODUCT DESCRIPTION

Hardwaxoil TITAN is a special oil suitable for oil finishing of wooden floors. Good filling properties, very natural colour, good chemical and mechanical resistance. The Hardwaxoil TITAN has a longer open time which makes it very appropriate to apply by roller and rollercoater.

The durability can be improved by adding hardener UA 5% (optional).

TECHNICAL DATA

VISCOSITY	+/- 50 SEC (DIN 4MM)
SOLID CONTENT	+/- 46% BY WEIGHT
DENSITY	+/-0.92 KG/L AT 20 °C
GLOSS	MATT / SILK / SATIN
COLOR	CLEAR

USAGE

Particularly suitable for oiling of parquet, wooden floors and Furniture. Gives the wood a very natural appearance and is easy to repair.

PREPARATION

Sand the surface using a 100-120 grit sandpaper and remove sanding dust before application.

USER TIPS

Before use, shake and stir the hardwaxoil well. Can be applied by polishing machine (white or beige pad), paintbrush, roller (microfiber 6mm is advised) or cloth.

At least 2 coats are recommended for hard wood such as oak. For soft wood multiple coats can be applied. For industrial use, please contact our Ciranova service centre.

DRYING TIMES

Can be overcoated after +/- 8 Hours. The drying time is very dependent on the applied quantity, the temperature and air ventilation in the room. In higher temperatures and better ventilated rooms the drying times will be reduced.

APPLYING QUANTITY

With roller: +/- 35-40g/m² | 25-30 m²/liter per coat

With buffing machine: +/- 20g/m² | 40-50 m²/liter per coat

MAINTENANCE

Clean regularly with flooringsoap Ciranova. Depending on the use of the floor, use maintenance oil 1 time a year. For thorough cleaning, use Intensive Cleaner Ciranova®.

ATTENTION: The hardwaxoil needs +/- 14 days to fully cure. Don't use any water or maintenance products on the floor during this period.

PRODUCT INFORMATION

Shelf life: up to 2 years in a well closed original packaging.

SPECIAL QUALITIES

Used cloths or pads should be plunged in water because of the danger of spontaneous combustion. We recommend Hardwaxoil Magic TITAN as topcoat on the pigmented Hardwaxoils.

Colored Hardwaxoils should always be tested before treating the entire surface. Used sanding grain, type of